



## Zetamix 17-4PH stainless steel datasheet

### PRODUCT DESCRIPTION

**Zetamix 17-4PH** is a stainless steel filament used for 3D printing. The binders mixed with stainless steel powder enables to have a flexible and resistant filament usable with classical FFF printers (Fused Filament Fabrication). Printed parts need to be debinded and sintered.

Diameter available: 1,75mm

Postprocess : chemical debinding and sintering

### IDENTIFICATION

Trade name	Zetamix 17-4PH stainless steel
Chemical name of raw material	17-4PH
Binding proportion (vol) %	40%
Binding proportion (mass) %	8%
17-4PH proportion (vol) %	60%
17-4PH proportion (mass) %	92%

## PRINTING AND SINTERING RECOMMANDATIONS

Printing temperature	110-150°C
Solvent debinding	Acetone at 40°C
Sintering temprature	1350°C, under hydrogenated argon
Shrinkage	x,y = 14.5% ±1% / z = 14.5% ±1%
Density	>90 %

## TYPICAL PROPERTIES OF THE FILAMENT

Specific Gravity [g.cm <sup>-3</sup> ]	4.80
Melt Flow Index [g/10(min)] (@120°C, 2.5kg, half-die)	30
Melt Volume Rate [cm <sup>3</sup> /10(min)]	6.3

Disclaimer : The results presented above are for information and do not constitute a legally binding Material Safety Data sheet (MSDS). Moreover, values are significantly dependent on printing and debinding parametters , operators experience and surrounding conditions. Any descriptions, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product.